

Characteristics and features

- soft natural rubber quality
- sulfur cured
- rebound > 65%
- PAH free acc. AfPS GS 2014: cat.1
- not discoloring
- short time temperature-resistant to +80°C

A-DA 40-82

All our products are:

- PAH-free (EU 1272/2013)
- REACH conform
- Nitrosamin free
- RoHS II conform

Technical data sheet

Polymer		DIN ISO 1629	NR
Colour			grey
Shore hardness	[ShA]	ISO 7619-1 / 3s	40 ± 5
Density	[g/cm ³]	DIN EN ISO 1183 / ISO 2781	0,99 ± 0,02
Tensile strength	[N/mm ²]	ISO 37	> 16
Elongation at break	[%]	ISO 37	> 500
Temperature resistance	[°C]		-40°C to +70°C
Tear strength	[N/mm]	DIN ISO 34-1 A	> 6,0
Compression set *	[%]	ISO 815	< 15
Fire resistance **		FMVSS 302	B (hardly inflammable)
Ozone resistance ***		ISO 1431-1	not ozone resistant
Spec. Volume resistance	[Ωcm]	VDE 0303-30	isolating

* 24 h / 70 °C; ** tested at bei 2 mm; *** 50 pphm, 40°C, 72 h, 20% Elongation

Resistance



Stand: 22.09.2016 / issue: 1

Important information:

The listed test values and data are based on results of many years of development, tests and proving. A characteristics warranty and guaranteed function can't be derived from the information given. It is within the user's responsibility to test the selection of material in a specific application to ascertain his intended operational capability. Technical changes within the product development are subject to change.

This edition supersedes all previous data sheets.